

www.rcrflooringproducts.com RCR Flooring Products Limited Mill Close, Lee Mill Industrial Estate, Ivybridge, Devon, PL21 9GL t: +44 1752 895288 | f: +44 1752 395800 | e: info@rcrflooringproducts.com



(\mathbf{r}) ermaban Signatur

Specification Sheet Issue 1.8 01/09/2024











All content found within this datasheet is approximate. RCR Flooring Products Ltd reserves the right to amend this datasheet at any time. For further details, please contact RCR Flooring Products Ltd. RCR Flooring Products Ltd is registered in England & Wales - No. 02815314.




Permaban Signature®

Specification Sheet Issue 1.8 01/08/2024

manufacturing tolerances Length ±2.0mm Height Straightness ±0.5mm/600mm ±1mm

dimensions of Permaban Signature®



dimensions in mm

dimensions and weight of Permaban Signature® Nominal Slab Joint Height, **Dowel Size** Dowel Length (mm) Single Joint Number Per Bundle Depth (mm) h (mm) (mm) Centres (mm) Weight (kg) Bundle Weight (kg) 125 24 28 797 150 26 45 1295 2100 175 20 x 20 x 420 300 28 45 1385 200 30 36 1205 225 1277 32 36

Typical height and length values shown only. Weight values and bundle information shown are approximate.

| materials | | | | |
|-------------------------|------------------------|--|--|--|
| Component | Material | | | |
| Sheet steel formwork | EN 10346:2015 DX51D+Z | | | |
| Reinforcement steel bar | BS 4449:2005 B500A | | | |
| Square dowel bar | EN 10025-2:2004 S275JR | | | |
| Square dowel bar sleeve | PP | | | |





All content found within this datasheet is approximate. RCR Flooring Products Ltd reserves the right to amend this datasheet at any time. For further details, please contact RCR Flooring Products Ltd. RCR Flooring Products Ltd is registered in England & Wales - No. 02815314.



Permaban Signature®

Specification Sheet Issue 1.8 01/08/2024

theoretical calculated ultimate loads at failure of dowel or concrete

| (For typical slabs, 40N/mm2 concrete and 20mm joint opening) | | Unreinforced Slab | |
|--|------------|-------------------|----------------|
| Slab Depth (mm) | Dowel Type | Bursting (kN/m) | Bending (kN/m) |
| 150 | Square Bar | 31.50 | 57.66 |
| 175 | Square Bar | 36.75 | 57.66 |
| 200 | Square Bar | 42 | 57.66 |
| 225 | Square Bar | 47.25 | 57.66 |
| 250 | Square Bar | 52.50 | 57.66 |
| 275 | Square Bar | 57.75 | 57.66 |
| 300 | Square Bar | 63 | 57.66 |

Ultimate load (kN/m)

This table shows the load at failure in bursting (failure of the concrete) and bending (failure of the dowel) for a joint opening of 20mm - larger joint openings can be accommodated. The ultimate load has been calculated in accordance with TR34 4th Edition. Dowel position taken at mid depth of slab. For more detailed analysis please contact RCR Flooring Products Ltd.

*All design calculations should be verified by a suitably qualified structural engineer.







All content found within this datasheet is approximate. RCR Flooring Products Ltd reserves the right to amend this datasheet at any time. For further details, please contact RCR Flooring Products Ltd. RCR Flooring Products Ltd is registered in England & Wales - No. 02815314.