

www.rcrflooringproducts.com RCR Flooring Products Limited Mill Close, Lee Mill Industrial Estate, Ivybridge, Devon, PL21 9GL t: +44 1752 895288 | f: +44 1752 395800 | e: info@rcrflooringproducts.com



ermaban signatur

Specification Sheet Issue 1.4 07/02/2019 •











All content found within this datasheet is approximate. RCR Flooring Products Ltd reserves the right to amend this datasheet at any time. For further details, please contact RCR Flooring Products Ltd. RCR Flooring Products Ltd is registered in England & Wales - No. 02815314.




permaban signature®

Specification Sheet Issue 1.4 07/02/2019

Imanufacturing tolerances Length ±2.0mm Height ±1mm Straightness ±0.5mm/600mm

dimensions of permaban signature®



300 square dowel bar centres

dimensions in mm

dimensions and weight of permaban signature®										
Nominal Slab Depth (mm)	Joint Height, h (mm)	Dowel Size (mm)	Dowel Centres (mm)	Length (mm)	Single Joint Weight (kg)	Number Per Bundle	Bundle Weight (kg)			
150	125	20 x 20 x 420	300	2100	23.4	54	1384 kg			
170	140				24.8	45	1290 kg			
190	160				26.7	45	1380 kg			
210	180				28.4	36	1215 kg			

Typical height and length values shown only. Weight values and bundle information shown are approximate.

materials						
Component	Material					
Sheet steel formwork	BS EN 10346: 2015 DX51D+Z					
Reinforcement steel bar	BS 4449:2005 B500A					
Square dowel bar	BS EN 10025-2:2004 S275JR					
Square dowel bar sleeve	PP					







All content found within this datasheet is approximate. RCR Flooring Products Ltd reserves the right to amend this datasheet at any time. For further details, please contact RCR Flooring Products Ltd. RCR Flooring Products Ltd is registered in England & Wales - No. 02815314.



permaban signature®

Specification Sheet Issue 1.4 07/02/2019

theoretical calculated ultimate loads at failure of dowel or concrete

(for typical slabs, 40N/mm2 concrete and 200mm joint opening)		Unreinforced Slab			
Slab Depth (mm)	Dowel Type	Bursting (kN/m)	Bearing/Bending		
150	Square Bar	31.5	342.1		
200	Square Bar	42	342.1		
250	Square Bar	52.5	342.1		
300	Square Bar	63	342.1		
350	Square Bar	72.5	342.1		

This table shows the load at failure in bursting (failure of the concrete) and bending (failure of the dowel) for a joint opening of 20mm - larger joint openings can be accommodated. The ultimate load has been calculated in accordance with TR34 4th Edition. Dowel position taken at mid depth of slab. For more detailed analysis please contact RCR Flooring Products Ltd.

*All design calculations should be verified by a suitably qualified structural engineer.

